

# SAVSOL FLUID 12WW

## DESCRIPTION:

SAVSOL FLUID 12WW is a mould releasing oil blending with highly refined base oil with premium additives to offer excellent oxidation stability and de-foaming properties.

## APPLICATION:

SAVSOL FLUID 12WW is used as mould releasing agent during the manufacture of glass products.

## ADVANTAGES:

SAVSOL FLUID 12WW offer the following benefits over conventional glass mould oils:

- Very low carbon formation and hence reduced mould cleaning.
- Reduced downtime.
- Minimal effect on environment and harmless to skin.
- Clear bottles.
- Extended mould life.

## TECHNICAL SPECIFICATIONS: SAVSOL FLUID 12WW

PROPERTIES	ASTM TEST METHOD	TYPICAL VALUES
Appearance	Visual	Clear & Bright
Colour ASTM	D1500	L0.5
Density @ 29.5 °C, gm/cm <sup>3</sup>	D1298	0.8330
Kinematic Viscosity @ 40°C, cSt	D445	12.20
Viscosity Index	D2270	110
Flash Point, COC, °C	D92	204
Pour Point, °C	D97	-24
Volatility, %	DIN 515 81	39.4
Copper Strip Corrosion Test	D130	Pass
Total Acid Number, mg KOH/gm	D664	0.01
Sulfur Content, ppm	D2622	<10
Carbon residue, % by wt	D189	<0.01



# SAVSOL FLUID 12WW

*The above details are typical results of normal production and variations in these characteristics may occur. The information contained herein is subject to change without notification. All recommendations and suggestions are without guarantee and the manufacturers do not accept liability for any loss or damage, however arising, which results directly from the use of such information, nor do we offer any warranty.*

## **Storage:**

Store the products indoors and avoid direct sunlight or heat. Please keep the container in closed condition always.

## **Environment, Health and Safety**

- Do not dispose the used oil to soil, drains and water. Dispose the used oil through authorized collection point
- This product is unlikely to present any safety & health hazard when properly used in the recommended application.
- Avoid contact with skin and eyes. After skin contact, wash with water and soap.

Rev.No.00 dtd 21<sup>st</sup> Aug. 2019